

Technical Product Data sheet 01.12

Product Name	Tinted Stabiliser
Product reference	PP21
Product description	Tinted Stabiliser is a pigmented solvent borne masonry binding primer based on acrylic resins. Improves adhesion of finishing coatings to porous and chalking masonry surfaces. Tinted Stabiliser provides an alkali resistant barrier where subsequent coatings are susceptible to alkali attack.
Uses	Primer/stabiliser for porous or chalky masonry surfaces
Pack sizes availability	20 litres
Colour range	Off White.
Specific gravity	Approx 1.3
Flash point	Flammable Flash point approx 40deg C
Recommended Spreading rate	Approx. 3 - 5 m <sup>2</sup> /litre
Solids content	Approx 65% w/w Approx 42% v/v
Drying time	Approx 4 hours 20°C 65%RH
Over-coating time	Approx 12 hours 20°C 65%RH
Minimum application temperature	The performance of Tinted Stabiliser is not adversely affected by low temperatures. However, do not apply during frosty or foggy weather or onto wet surfaces
Recommended dry film thickness	Approximately 100 microns
Method of application	Brush, roller or airless spray

Preparation	<p>Surfaces must be clean, sound and dry and prepared in accordance with BS6150 Painting of buildings – code of practice.</p> <p>Treat organic growth with fungicidal solution.</p> <p>Remove any unsound previous coating and weak material and repair with suitable exterior repair products before coating with Tinted Stabiliser.</p>
Storage life	<p>Min 12 months in original sealed containers.</p> <p>Protect from frost and direct heat</p>
Thinning/cleaning	<p>Thin where necessary with D40 Solvent or white spirit. Do not exceed 1 part solvent to 20 parts of Tinted Stabiliser.</p> <p>Wash equipment immediately after use with D40 solvent or white spirit.</p>
Safety precautions	Refer to the safety data sheet before use
Volatile organic content (voc)	<p>Limit for this product Cat A/h 750g/l (2010).</p> <p>This product contains maximum 450g/l VOC</p>
Disposal	<p>When this coating, in its liquid state, as supplied or skinned, becomes a waste, it is categorised as hazardous waste, with code 08 01 11 (list of hazardous wastes)</p> <p>Used containers, drained and/or rigorously scraped out and containing dried residues of the supplied coating, are categorised as non-hazardous waste, with code 15 01 04 (list of wastes)</p> <p>If mixed with other wastes the above waste codes may not be applicable</p>