

Technical Product Data sheet 01.12

Product Name	High-build Texture S/B masonry coating
Product reference	PP40
Product description	Solvent borne high build textured masonry coating formulated for trowel and roll application. Based on modified acrylic resins, High-build Texture S/B exhibits excellent adhesion to most masonry surfaces and may be textured using appropriate rollers to provide attractive finishes.
Uses	Decorative protective coating for exterior masonry surfaces
Pack sizes availability	20 litres
Colour range	As colour card. Special colours on request subject to minimum batch sizes
Specific gravity	Approx 1.5
Flash point	Flammable Flash point approx 40deg C
Recommended Spreading rate	Approx. 1 litre/m ²
Solids content	Approx 70% w/w Approx 54% v/v
Drying time	Approx 24 hours 20°C 65%RH 2 – 3 weeks for full curing
Over-coating time	Normally applied as a single coat
Minimum application temperature	The performance of High-build Texture S/B is not adversely affected by low temperatures. However, do not apply during frosty or foggy weather or onto wet surfaces
Recommended dry film thickness	Approximately 700 microns

Method of application	Trowel and roller
Preparation	<p>Surfaces must be clean, sound and dry and prepared in accordance with BS6150 Painting of buildings – code of practice.</p> <p>Treat organic growth with fungicidal solution.</p> <p>Remove any unsound previous coating and weak material and repair with suitable exterior repair products before coating.</p>
Storage life	<p>Min 12 months in original sealed containers.</p> <p>Protect from frost and direct heat</p>
Thinning/cleaning	<p>Thin where necessary with D40 Solvent or white spirit. Do not exceed 0.5 parts solvent to 20 parts of High Build Texture S/B.</p> <p>Wash equipment immediately after use with D40 solvent or white spirit.</p>
Safety precautions	Refer to the safety data sheet before use
Volatile organic content (voc)	<p>Limit for this product Cat A/c 430g/l (2010).</p> <p>This product contains maximum 430g/l VOC</p>
Disposal	<p>When this coating, in its liquid state, as supplied or skinned, becomes a waste, it is categorised as hazardous waste, with code 08 01 11 (list of hazardous wastes)</p> <p>Used containers, drained and/or rigorously scraped out and containing dried residues of the supplied coating, are categorised as non-hazardous waste, with code 15 01 04 (list of wastes)</p> <p>If mixed with other wastes the above waste codes may not be applicable</p>